



Custom Work Deserves a Custom Bond

FSV ADHESIVE

FLEXIBLE SHEET VENEER ADHESIVE

TYPE: Synthetic Resin Dispersion

TECHNICAL DATA:

Viscosity	Cps	7500-8500
Solids	%	52-58
Minimum Use Temperature		55°F
Freeze Thaw Stable	5 cycles	No
Storage Life @ 70°F		6 months
Color		Light pink

CHARACTERISTICS: FSV Adhesive is a high quality synthetic resin dispersion cold setting adhesive. It is specially formulated for use with a wide range of flexible sheet veneers. Particleboard, MDF, and other wood component cores can be used in a nip roll or hand roll application process where fast tack and quick set with minimum pressure is required. This product is also suitable for use with high pressure laminates.

APPLICATIONS: For application of flexible sheet veneer to a wide range of substrates and for lamination of HPL to flat wood based composite cores. Also for cold press applications.

- ADVANTAGES:**
- Environmentally friendly – no voc, non-polluting
 - Quick tack, fast set
 - Light pink for ease of visibility
 - Good gap filling properties
 - Good heat resistance
 - Flexible bond

- DIRECTIONS FOR USE:**
- All wood substrates should be conditioned at room temperature at 6-9% moisture content
 - A 20-35 lbs/msgl or 4-7 mil spread is adequate applied by roller
 - Laminate is then applied to substrate allowing a maximum open assembly time of 5 minutes but is dependent on porosity of the substrates, room temperature, and quantity applied
 - Allow a maximum closed assembly time of 10-15 minutes prior to running through the nip roller.
 - While the glue is still wet The panel is then passed through a nip roller. Glue should be “wet” when the assembly is passed through the nip roller.
 - Note: Nip rolling can be accomplished with effectively no open/ closed assembly time. However, the best initial tack and final bond occurs through the use of maximum open and closed assembly times.
 - Panels may be dead stacked allowing a set time of about 45 minutes to 1 hour. A 24 hour cure time is recommended before machining. No additional pressure is required.

CLEANUP: If the adhesive is still liquid, use warm water. Dried adhesive can be removed with hot water. For waste disposal, compliance with all applicable federal, state and local regulation must be observed.

STORAGE: FSV can be stored in factory sealed containers for 6 months at 77°F. Protect from frost.